

DURATION® T80

Premium Water Borne Fluorinated Polymer Finish

PC 865

- FEATURES**
- EXCELLENT UV RESISTANCE AND GLOSS RETENTION
 - VERY SHORT RECOAT TIME WHEN APPLYING WET ON WET
 - VERY LOW VOC & LOW ODOUR
 - TINTABLE – AVAILABLE IN OVER 5,000 COLOURS
 - VERY GOOD ANTI GRAFFITI PROPERTIES

USES DURATION® T80 is a premium, two-component, water borne, fluorinated polymer finish that demonstrates excellent gloss and colour retention and is designed for applications where extended service periods are required. This is delivered via a system with a very low VOC content of only 23 grams per litre. DURATION® T80 is formulated to be used as part of complete DURATION® water borne protective coatings system for steel that is subject to sheltered or mild (C1-C3) corrosive environments including residential and commercial construction, hospitals, warehouses, schools, shopping centres and factories.

DURATION® T80 can also be used directly over Dulux® solvent borne epoxy primers, universal primers, epoxy intermediates and to aged, tightly adhering coatings subject to necessary solvent resistance tests and appropriate surface preparation.

SPECIFICATIONS

RESISTANCE GUIDE

WEATHERABILITY	Excellent gloss and colour retention on exterior exposure	SOLVENTS	Unaffected by splash and spillage of common alcohols, aliphatic and aromatic hydrocarbons, esters and ketones
HEAT RESISTANCE	Up to 120°C dry heat.	WATER	Excellent resistance to fresh and salt water but not suitable for immersion.
SALTS	Unaffected by splash and spillage of most salt solutions	ALKALIS	Good resistance to splash and spillage of most common alkalis
ACIDS	Suitable for splash and spillage exposure to most acids	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	Two pack fluoropolymer		APPLICATION CONDITIONS			
FINISH	Gloss and Satin			Min	Max	
COLOUR	Extensive range of colours using the Dulux Authentic Colour® Low VOC Tint System.		Air Temp.	10°C	40°C	
			Substrate Temp.	10°C	40°C	
			Relative Humidity		85%	
COMPONENTS	Two		COATING THICKNESS (MICRONS)			
VOLUME SOLIDS	40% (Vivid white)			Min	Max	Recommended
VOC LEVEL	23 g/L		Wet film per coat (µm)	120	190	120
FLASH POINT	N/A		Dry film per coat (µm)	50	75	50
POT LIFE	1 hour (4 litre kit, 25°C)		SUITABLE SUBSTRATES	Suitably primed steel, aluminium, zinc coated steel, concrete and MDF		
MIXING RATIO V/V	Part A : 5	Part B : 1	PRIMERS	Epoxy primers, etch primers and universal metal primers		
THINNER –BRUSH	Potable Water		APPLICATION METHODS	Air spray, airless, roller and brush		
THINNER –SPRAY	Potable Water					
PRODUCT CODE	H25-04912	Gloss Vivid White Base				
	H25-16101	Gloss Ultra Deep Tone Base				
	H25-87663	Gloss Extra Bright Base				
	H26-04912	Satin Vivid White Base				
	H26-16101	Satin Ultra Deep Tone Base				
	H26-87663	Satin Extra Bright Base				
	976-H0182	Standard Hardener				

DRYING CHARACTERISTICS AT 50 µm DRY FILM THICKNESS*

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min ¹	Max ²
25° C	50%	45 Minutes	24 Hours	7 Days	24 Hours	3 days

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹ The product can also be applied **wet on wet**, see the **Application** section for further advice.

² If the maximum overcoat interval is exceeded then the surface **MUST** be abraded to ensure maximum intercoat adhesion.

SPREADING RATE ASSUMING NO LOSSES

8.0 square metres per litre equals 50 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as colour, application method, ambient conditions and surface porosity and roughness.

DURATION® T80

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)	
STEEL - NEW	Low-medium corrosivity (AS2312.1 Cat C1-C3)	Abrasive blast AS1627.4 Class 2.5	1 st Coat	Duration® P23	75 µm
			2 nd Coat	Duration® X21	50 µm
			3 rd Coat	Duration® T80	50 µm
GALVANISED STEEL	Exterior	Degrease and whip blast	1 st Coat	Duration® P23	75 µm
			2 nd Coat	Duration® X21	50 µm
			3 rd Coat	Duration® T80	50 µm
ALUMINIUM	Exterior/Interior	Clean, degrease and abrade surface	1 st Coat	Duration® P23	75 µm
			2 nd Coat	Duration® X21	50 µm
			3 rd Coat	Duration® T80	50 µm
MDF	Interior	Sand and dust down before and after first coat	1 st Coat	Luxepoxy® 4 White Primer	50 µm
			2 nd Coat	Duration® X21	50 µm
			3 rd Coat	Duration® T80	50 µm

NOTE: If application is by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity

SURFACE PREPARATION	<p>Specifiers should follow the surface preparation guidelines from the data sheet for the first coat selected. The surface must be sound and free from grease, oil, dirt, rust, loose paint and other contaminants. Dulux® recommends that surfaces be degreased with Gamlen CA 1 detergent (according to the manufacturer's written instructions and all safety warnings) and then abraded to provide a key for the coating system.</p>											
APPLICATION	<p>Mix part A and part B thoroughly using a power mixer until the contents of each part is uniform. Ensure bases have been tinted to the correct colour before use. DULUX® ASSUMES NO RESPONSIBILITY FOR THE APPLICATION OF INCORRECT COLOUR. Mix the contents of both packs together thoroughly using a power mixer. DO NOT RINSE OUT THE PART B (ISOCYANATE COMPONENT) CAN WITH WATER. Then thin with water if required under mixing. Please ensure that mixing does not generate an excessive amount of foam. Let stand for 10 minutes. Box all containers before use to ensure colour consistency. Remix thoroughly before application.</p>											
BRUSH/ROLLER	<p>Application can be improved by thinning the mixed product with up to 150 ml/litre with potable water. When brushing and rolling additional coats may be required to attain the specified thickness.</p>											
SPRAY GENERAL	<p>The product can also be applied wet on wet, please refer to the following flash off times as a guide to apply additional coats wet on wet.</p> <table border="1"> <thead> <tr> <th>Temperature</th> <th>10° C</th> <th>25° C</th> <th>40° C</th> </tr> </thead> <tbody> <tr> <td>Time</td> <td>2 Hours</td> <td>45 minutes</td> <td>20 minutes</td> </tr> </tbody> </table>			Temperature	10° C	25° C	40° C	Time	2 Hours	45 minutes	20 minutes	
Temperature	10° C	25° C	40° C									
Time	2 Hours	45 minutes	20 minutes									
CONVENTIONAL SPRAY	<p>When thinning the mixed product with up to 150ml/litre with potable water to aid atomisation. Apply in multiple wet coats overlapping each pass 50%.</p> <table border="1"> <thead> <tr> <th>Typical Set-up</th> <th>Graco AirPro</th> <th>1.4mm (239542)</th> </tr> </thead> <tbody> <tr> <td></td> <td>Pressure at Triton 308:</td> <td>70-100 kPa (10-15 p.s.i.)</td> </tr> <tr> <td></td> <td>Pressure at Gun:</td> <td>380-410 kPa (55-60 p.s.i.)</td> </tr> </tbody> </table>			Typical Set-up	Graco AirPro	1.4mm (239542)		Pressure at Triton 308:	70-100 kPa (10-15 p.s.i.)		Pressure at Gun:	380-410 kPa (55-60 p.s.i.)
Typical Set-up	Graco AirPro	1.4mm (239542)										
	Pressure at Triton 308:	70-100 kPa (10-15 p.s.i.)										
	Pressure at Gun:	380-410 kPa (55-60 p.s.i.)										
AIRLESS SPRAY	<p>Standard airless spray equipment such as a Graco Xtreme 30:1 with a fluid tip of 15 thou (0.38) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Thinning is not normally required but up to 150 ml/litre of potable water may be added to aid application.</p>											
PRECAUTIONS	<p>This is an industrial product designed for use by experienced Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Consultant for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the written consent of Dulux® Australia. Do not use any product past its pot life. Product past its pot life may still appear fit for use but will develop substantially reduced gloss and may develop brittleness. Freshly mixed material must not be added to material that has been mixed for some time. The rate of cure is dependent upon temperature. Do not apply at temperatures below 10°C, or where the surface temperature is below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Ensure you read and understand the safety precautions on the Material Safety Data Sheets for the two components before using. You should only thin the mixed product with potable water. Do not add water to the PART B, isocyanate component.</p>											
CLEAN UP	<p>Clean all equipment with clean warm water immediately after use followed by DULUX® EPOXY THINNER (920-08925).</p>											
OVERCOATING	<p>Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating. Epoxies must be abraded if recoated outside the recoat window.</p>											

DURATION® T80

SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au
STORAGE	Both components are NOT classified as dangerous goods for transport or storage. Store in well ventilated bunded area under cover and away from sources of heat. Keep containers closed at all times.
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.
FLAMMABILITY	This product is not flammable. On burning will emit toxic fumes.
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

COMPANY INFORMATION		PACKAGING, TRANSPORT AND STORAGE	
Dulux Protective Coatings a division of		PACKAGING	Available in 4 litre and 20 litre packs
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	TRANSPORTATION WEIGHT	1.35 kg/litre (Average of components)
		DANGEROUS GOODS	Part A: Non Dangerous Goods Part B: Non Dangerous Goods

Dulux, Dulux Authentic Colour, Duration and Luxepoxy are registered trade marks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.