

# HI TEMP™ 400

## Silicone Based High Temperature Coating

PC 929

- FEATURES**
- SUITABLE FOR OPERATING TEMPERATURES TO 435°C
  - SINGLE PACK
  - SELF PRIMING TOPCOAT
  - SUITABLE FOR INTERIOR AND EXTERIOR

**USES** HI TEMP™ 400 is recommended for service temperatures to 435°C. Typical applications include furnace equipment, reaction vessels, boiler fronts, hot metal stacks, kilns, flues and exhaust systems.  
Prior to application of HI TEMP™ 400 to a surface operating above 205°C it is essential that the surface be prepared to recommended abrasive blast clean standards.

### SPECIFICATIONS

#### RESISTANCE GUIDE

<b>WEATHERABILITY</b>	Good	<b>SOLVENTS</b>	Good resistance to solvent fumes only
<b>HEAT RESISTANCE</b>	100°C to 435°C dry heat	<b>WATER</b>	Resists rain and condensation. Not recommended for permanently damp or immersed exposure
<b>SALTS</b>	Unaffected by splash and spillage of neutral salt solutions	<b>ALKALIS</b>	Excellent resistance to mild industrial alkali fumes
<b>ACIDS</b>	Excellent resistance to mild industrial acid fumes	<b>ABRASION</b>	Good when fully cured

#### TYPICAL PROPERTIES AND APPLICATION DATA

<b>CLASSIFICATION</b>	Silicone high temperature coating		<b>APPLICATION CONDITIONS</b>			
<b>FINISH</b>	Flat			Min	Max	
<b>COLOUR</b>	Black and Aluminium		<b>Air Temp.</b>	10°C	45°C	
			<b>Substrate Temp.</b>	10°C	45°C	
			<b>Relative Humidity</b>		85%	
<b>COMPONENTS</b>	One		<b>COATING THICKNESS (MICRONS)</b>			
<b>VOLUME SOLIDS</b>	13% (Black), 15% (Aluminium)			Min	Max	Recommended
<b>VOC LEVEL</b>	<750 g/L (Black)		<b>Wet film per coat (µm)</b>	70	200	135
<b>FLASH POINT</b>	27°C		<b>Dry film per coat (µm)</b>	10	30	20
<b>POT LIFE</b>	Not applicable		<b>SUITABLE SUBSTRATES</b>	Abrasive blast cleaned steel		
<b>MIXING RATIO V/V</b>	Single Pack		<b>PRIMERS</b>	Self priming, Hi Temp™ Uniprime, or Durezinc® i90		
<b>THINNER</b>	965-63020	Dulux® CR Reducer	<b>TOPCOATS</b>	Not applicable		
<b>PRODUCT CODE</b>	950-89786	Black	<b>APPLICATION METHODS</b>	Brush, roller, conventional, airless spray or air assisted spray		
	950-89787	Aluminium				

#### DRYING CHARACTERISTICS AT 20 µm DRY FILM THICKNESS\*

Temperature	Humidity	Touch	Handle	Full Cure <sup>1</sup>	OVERCOAT	
					Min	Max <sup>2</sup>
25° C	50%	2 Hours	24 Hours	On Heating	6 Hours	Until Heated

\* These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

<sup>1</sup> Product does not fully harden and develop full protective properties until the surface is heated to 150°C to 200°C for 1 hour.

<sup>2</sup> If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

**SPREADING RATE** 7.5 square metres per litre equals 20 µm dry film thickness

ASSUMING NO LOSSES

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

# HI TEMP™ 400

## TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
STEEL – NEW	150°C – 400°C	Abrasive blast clean AS1627.4 Class 2.5	1 <sup>st</sup> Coat Durezinc™ i90 2 <sup>nd</sup> Coat Hi Temp™ 400 3 <sup>rd</sup> Coat Hi Temp™ 400	75 µm 20 µm 20 µm
STEEL – NEW	150°C – 435°C	Abrasive blast clean AS1627.4 Class 2.5	1 <sup>st</sup> Coat Hi Temp™ 400 2 <sup>nd</sup> Coat Hi Temp™ 400	20 µm 20 µm
STEEL – NEW	150°C – 435°C	Abrasive blast clean AS1627.4 Class 2.0	1 <sup>st</sup> Coat Hi Temp™ Uniprime 2 <sup>nd</sup> Coat Hi Temp™ 400 3 <sup>rd</sup> Coat Hi Temp™ 400	25 µm 20 µm 20 µm

NOTE: If application is by brush or roller, additional coats will be necessary to achieve the minimum DFT

<b>SURFACE PREPARATION</b>	Specifiers should follow the surface preparation guidelines from the data sheet for the primer or first coat selected. <b>Steel:</b> Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Degrease with Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's data sheet. Abrasive blast clean to a minimum of AS1627.4 Class 2.5. <b>Steel where abrasive blast cleaning is not viable:</b> Rust, mill scale, oxide deposits and old paint films on metal surfaces must be removed by power tool cleaning according to AS1627.2 Class 2.
<b>APPLICATION BRUSH/ROLLER</b>	Mix each can thoroughly using a power mixer until the contents are uniform. Remix thoroughly before application. Brushing is the preferred method of application of the first coat. Apply even coats of the mixed material to the prepared surface. When brushing and rolling additional coats may be required to attain the specified thickness.
<b>CONVENTIONAL SPRAY</b>	Thin up to 100ml/litre with Dulux® CR Reducer (965-63020) to aid atomisation. Apply in multiple wet coats overlapping each pass 50%. Typical Set-up Graco AirPro 1.4mm (239542) Pressure at Triton 308: 70-100 kPa (10-15 p.s.i.) Pressure at Gun: 340-410 kPa (50-60 p.s.i.)
<b>AIRLESS SPRAY</b>	Standard airless spray equipment such as a Graco Xtreme 30:1 with a fluid tip of 13 thou (0.33mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Thinning is not normally required but up to 50 ml/litre of Dulux® CR Reducer (965-63020) may be added to aid application.
<b>PRECAUTIONS</b>	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the written consent of Dulux® Australia. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Allow at least 8 hours drying of the final coat before heating up. After this initial drying period, increase temperatures gradually until 150°C is reached. The coating does not fully harden and develop full protective properties until the surface is heated to 150°C to 200°C for at least 1 hour. Where frequent shut down of plant occurs in aggressive industrial or marine environments, maximum corrosion resistance will be given by priming with DUREZINC® i90. Film thicknesses are critical to sound performance; over-thick films will cause blistering on heat-up. Care should be taken when overcoating to avoid pick-up of the first coat. For this reason the second coat is best applied by spray. Not suitable for use under insulation where moisture is present.
<b>CLEAN UP</b>	Clean all equipment with Dulux® CR Reducer (965-63020) immediately after use.
<b>OVERCOATING</b>	Do not overcoat with itself once the coating has been heat cured. Rust, mill scale, oxide deposits and old paint films on metal surfaces must be removed by abrasive blast cleaning to AS1627.4 Class 2.5.
<b>SAFETY PRECAUTIONS</b>	<b>Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or <a href="http://www.duluxprotectivecoatings.com.au">www.duluxprotectivecoatings.com.au</a></b>
<b>STORAGE</b>	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
<b>HANDLING</b>	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
<b>USING</b>	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.
<b>FLAMMABILITY</b>	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO <sub>2</sub> or dry chemical powder. On burning will emit toxic fumes.
<b>WELDING</b>	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

## COMPANY INFORMATION

Dulux Protective Coatings a division of

DuluxGroup (Australia) Pty Ltd  
1956 Dandenong Road, Clayton 3168  
A.B.N. 67 000 049 427

DuluxGroup (New Zealand) Pty Ltd  
150 Hutt Park Road, Lower Hutt, NZ  
A.B.N. 55 133 404 118

## PACKAGING, TRANSPORT AND STORAGE

PACKAGING Available in 4 litre containers

TRANSPORTATION WEIGHT 1.03 kg/litre

DAINGEROUS GOODS Class 3 UN 1263

Dulux, and Durezinc are registered trade marks of DuluxGroup (Australia) Pty Ltd. DuluxGroup and Hi Temp are trade marks.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.