

# DUREMAX<sup>®</sup> GFX

## High Performance Surface Tolerant Glass Flake Epoxy

PC 256

- FEATURES**
- HIGH GLASS FLAKE CONTENT - EXCELLENT BARRIER FOR IMMERSION OR SPLASH ZONE
  - SUPERIOR RESIN TECHNOLOGY FOR SURFACE WETTING AND CORROSION RESISTANCE
  - HIGH PERFORMANCE MAINTENANCE COATING FOR NEW OR EXISTING STEEL
  - SELF PRIMING FINISH – HIGH SOLIDS AND HIGH BUILD FORMULATION
  - GOOD ABRASION AND CHEMICAL RESISTANCE

**USES** DUREMAX<sup>®</sup> GFX is a high solids, high build glass flake reinforced epoxy developed to deliver long term corrosion resistance. Ideally suited to protecting new steelwork from atmospheric and marine corrosion including coastal and off-shore structures, above and below the water-line.

The adhesion strength of DUREMAX<sup>®</sup> GFX allows it to be used as a high performance maintenance coating over hand, power tool or high-pressure water cleaned surface. DUREMAX<sup>®</sup> GFX can be topcoated with a wide range of coating types.

**SPECIFICATIONS** AS 3750.1-1994 "Paints for steel structures - Epoxy mastic (two-pack) - For rusted steel"  
 AS 4352-2005 "Tests for Coating Resistance to Cathodic Disbondment". Group A classification (When applied in two coats at 250 µm DFT per coat directly applied to abrasive blast cleaned steel - AS1627.4 Class 3)  
 AS/NZ 4020:2005 - suitable for use with potable water when using untinted Mid Grey cured with Standard Hardener or Cold Cure Hardener. Refer to your Dulux Protective Coatings Consultant for details.

### RESISTANCE GUIDE

<b>WEATHERABILITY</b>	Will yellow with time and chalk on exterior exposure. Neither yellowing nor chalking detracts from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	<b>SOLVENTS</b>	Resists splash and spillage of most hydrocarbon solvents, refined petroleum products and most common alcohols
<b>HEAT RESISTANCE</b>	Up to 120°C dry heat	<b>WATER</b>	Excellent resistance to immersion in fresh and salt water
<b>SALTS</b>	Excellent resistance to neutral and alkaline salts	<b>ALKALIS</b>	Good resistance to splash and spillage of strong alkalis
<b>ACIDS</b>	Suitable for splash and spillage of mild acids	<b>ABRASION</b>	Good when fully cured

### TYPICAL PROPERTIES AND APPLICATION DATA (STANDARD HARDENER)

<b>CLASSIFICATION</b>	Two Pack Glass Flake Reinforced Epoxy	<b>APPLICATION CONDITIONS</b>			
<b>FINISH</b>	Semi Gloss		Min	Max	
<b>COLOUR</b>	Mid Grey and Black	<b>Air Temp.</b>	10°C	45°C	
		<b>Substrate Temp.</b>	10°C	45°C	
		<b>Relative Humidity</b>		85%	
		<b>Concrete Moisture</b>		<10%	
<b>COMPONENTS</b>	Two	<b>COATING THICKNESS (MICRONS)</b>			
<b>VOLUME SOLIDS</b>	84% (Black)		Min	Max	Recommended
<b>VOC LEVEL</b>	<210 g/L (Black)	<b>Wet film per coat (µm)</b>	240	600	300
<b>FLASH POINT</b>	>23°C	<b>Dry film per coat (µm)</b>	200	500	250
<b>POT LIFE</b>	90 minutes (4 litre kit, 25°C)				
<b>MIXING RATIO V/V</b>	Part A : 4    Part B : 1	<b>SUITABLE SUBSTRATES</b>	Prepared rusty steel, aged tightly adhering coatings, prepared concrete Aluminium and galvanised steel		
<b>THINNER</b>	920-08925    Dulux <sup>®</sup> Epoxy Thinner	<b>PRIMERS</b>	Most Dulux <sup>®</sup> two pack primers		
<b>THINNER - IMMERSION</b>	965-63020    Dulux <sup>®</sup> CR Reducer	<b>APPLICATION METHODS</b>	Conventional, airless, or air assisted spray		
<b>PRODUCT CODE</b>	775-H0095    Mid Grey 775-H0094    Black 976-H0096    Standard Hardener 976-H0126    Cold Cure Hardener				

### DRYING CHARACTERISTICS AT 250 µm DRY FILM THICKNESS\* (STANDARD HARDENER)

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max <sup>1</sup>
10° C	50%	14 Hours	36 Hours	7 Days	36 Hours	4 Weeks
15° C	50%	10 Hours	24 Hours	7 Days	24 Hours	4 Weeks
25° C	50%	6 Hours	14 Hours	7 Days	14 Hours	4 Weeks

\*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

<sup>1</sup>If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

**SPREADING RATE**  
with Standard Hardener  
assuming no losses

**3.4 square metres per litre equals 250 µm dry film thickness**

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

# DUREMAX<sup>®</sup> GFX

## COLD CURE HARDENER

### COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	240	600	300
Dry film per coat (µm)	200	500	250

### APPLICATION CONDITIONS

	Min	Max
Air Temperature	5°C	45°C
Substrate Surface Temperature	5°C	45°C
Relative Humidity		85%
Concrete Moisture Content		<10%

SOLIDS BY VOLUME	84% (Black)
VOC LEVEL	<190 g/L (Black)
FLASH POINT	>23°C
POT LIFE	60 minutes (4 litre kit, 25°C)

## DRYING CHARACTERISTICS AT 250 µm DRY FILM THICKNESS\* (COLD CURE HARDENER)

### OVERCOAT

Temperature	Humidity	Touch	Handle	Full Cure	Min	Max <sup>1</sup>
5° C	50%	14 Hours	28 Hours	7 Days	28 Hours	4 Weeks
10° C	50%	13 Hours	24 Hours	7 Days	24 Hours	4 Weeks
15° C	50%	12 Hours	18 Hours	7 Days	18 Hours	4 Weeks
25° C	50%	6 Hours	9 Hours	7 Days	9 Hours	4 Weeks

\*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying

<sup>1</sup> If the maximum overcoat interval is exceeded then the surface **MUST** be abraded to ensure maximum intercoat adhesion

Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level

NOTE: Figures shown are for non-immersion conditions. Refer to PRECAUTIONS section for overcoating intervals and requirements for immersion service

### SPREADING RATE

with Cold Cure Hardener  
assuming no losses

**3.4 square metres per litre equals 250 µm dry film thickness**

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

## TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
STEEL – NEW OR MAINTENANCE	Immersion AS2312.1 Table C1 System EVH3	Abrasive blast clean AS1627.4 Class 3.0	1 <sup>st</sup> Coat Duremax <sup>®</sup> GFX 2 <sup>nd</sup> Coat Duremax <sup>®</sup> GFX	250 µm 250 µm
STEEL – NEW	Very high corrosivity (AS2312.1 Cat C5) Exceeds System EHB6	Abrasive blast clean AS1627.4 Class 2.5	1 <sup>st</sup> Coat Zincode <sup>®</sup> 402 2 <sup>nd</sup> Coat Duremax <sup>®</sup> GFX 3 <sup>rd</sup> Coat Duremax <sup>®</sup> GFX	75 µm 250 µm 250 µm
STEEL – NEW	Very high corrosivity (AS2312.1 Cat C5) System EVH3	Abrasive blast clean AS1627.4 Class 2.5	1 <sup>st</sup> Coat Durepon <sup>®</sup> P14 2 <sup>nd</sup> Coat Duremax <sup>®</sup> GFX 3 <sup>rd</sup> Coat Duremax <sup>®</sup> GFX	75 µm 400 µm
STEEL – MAINTENANCE	Exterior	Power tool clean AS1627.2 St 3 or Abrasive blast AS1627.4 Class 2	1 <sup>st</sup> Coat Duremax <sup>®</sup> GFX 2 <sup>nd</sup> Coat Duremax <sup>®</sup> GFX	250 µm 250 µm
CONCRETE	Exterior/Interior	Remove release agents and other surface contaminants	1 <sup>st</sup> Coat Duremax <sup>®</sup> GFX (Thin 10-15%) 2 <sup>nd</sup> Coat Duremax <sup>®</sup> GFX	250 µm 250 µm
ALUMINIUM	Exterior/Interior	Clean, degrease and abrade surface	1 <sup>st</sup> Coat Duremax <sup>®</sup> GFX	250 µm

NOTE: If application is by brush or roller, additional coats will be necessary to achieve the minimum DFT

# DUREMAX® GFX

<b>SURFACE PREPARATION</b>	<p><b>Steel:</b> Round off all rough welds, sharp edges and remove weld spatter. Remove contaminants in accordance with AS1627.1 Part 2.2 with Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's written instructions and all safety warnings. Abrasive blast clean to AS1627.4 Class 2.5 minimum.</p> <p><b>Immersed steel:</b> Abrasive blast cleaned to AS1627.4 Class 3. Remove all dust by brushing or vacuum cleaning.</p> <p><b>Steel where abrasive blast cleaning is not viable:</b> Rust, mill scale, oxide deposits and old paint films on metal surfaces must be removed by power tool cleaning according to AS1627.2. Coating performance is proportional to the degree of surface preparation.</p> <p><b>Steel Maintenance:</b> Wash with Gamlen CA 1 according to the manufacturer's written instructions and all safety warnings. (Refer to AS1627.1 Part 2.2). Remove unsound coatings. Feather back edges to remove ridges. Abrade entire surface of tightly adhering remaining coating to provide a suitable key for the new coating system. Remove all red rust by power tool cleaning in accordance with AS/NZ 1627:2 Class 2. Remove all residues. Spot prime bare steel.</p> <p><b>Concrete:</b> Concrete must be at least 28 days old before coating. Remove all laitance, form release, curing compounds, oil, grease and other surface contaminants. Fill any large cracks or voids using Luxepoxy® Filler.</p>														
<b>APPLICATION</b>	Stir each can thoroughly until the contents are uniform. Use of a power mixer is recommended. Mix the contents of both packs together thoroughly using a power mixer and allow to stand for 10 minutes. Remix thoroughly before using.														
<b>BRUSH/ROLLER</b>	Apply even coats of the mixed material to the prepared surface. When brushing and rolling additional coats may be required to attain the specified thickness.														
<b>CONVENTIONAL SPRAY</b>	Thinning is not normally required, however a small amount (5% or less by volume) of Dulux® Epoxy Thinner (920-08925) can be added.														
<b>AIRLESS SPRAY</b>	<table border="0"> <tr> <td>Typical Set-up</td> <td>Graco AirPro:</td> <td>1.8mm (239542)</td> </tr> <tr> <td></td> <td>Pressure at Triton 308:</td> <td>65-100 kPa (10-15 p.s.i.)</td> </tr> <tr> <td></td> <td>Pressure at Gun:</td> <td>385-420 kPa (55-60 p.s.i.)</td> </tr> </table>	Typical Set-up	Graco AirPro:	1.8mm (239542)		Pressure at Triton 308:	65-100 kPa (10-15 p.s.i.)		Pressure at Gun:	385-420 kPa (55-60 p.s.i.)					
Typical Set-up	Graco AirPro:	1.8mm (239542)													
	Pressure at Triton 308:	65-100 kPa (10-15 p.s.i.)													
	Pressure at Gun:	385-420 kPa (55-60 p.s.i.)													
<b>PRECAUTIONS</b>	Standard airless spray equipment such as a Graco Xtreme 45:1 or 56:1 with a fluid tip of 17–21 thou (0.43- 0.53mm) and an air supply capable of delivering 550-690 kPa (80 -100 psi) at the pump. Thinning is not normally required but up to 50ml/litre of Dulux® Epoxy Thinner (920-08925) may be added to ease application.														
<b>CLEAN UP</b>	Clean all equipment with Dulux® Epoxy Thinner (920-08925) immediately after use.														
<b>OVERCOATING</b>	Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating. Epoxies must be abraded if recoated outside the recoat window.														
<b>SAFETY PRECAUTIONS</b>	<b>Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or <a href="http://www.duluxprotectivecoatings.com.au">www.duluxprotectivecoatings.com.au</a></b>														
<b>STORAGE</b>	Store as required for a flammable liquid Class 3 in a bonded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.														
<b>HANDLING</b>	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.														
<b>USING</b>	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.														
<b>FLAMMABILITY</b>	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO2 or dry chemical powder. On burning will emit toxic fumes.														
<b>WELDING</b>	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.														
<b>COMPANY INFORMATION</b>															
<table border="0" style="width: 100%;"> <tr> <td colspan="2">Dulux Protective Coatings a division of</td> <td style="text-align: right;"><b>PACKAGING, TRANSPORT AND STORAGE</b></td> </tr> <tr> <td>DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427</td> <td>DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118</td> <td> <table border="0"> <tr> <td>PACKAGING</td> <td>Available in 15 litre packs</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.61 kg/litre (Average of components)</td> </tr> <tr> <td>DA</td> <td>Part A: Class 3 UN 1263</td> </tr> <tr> <td>DD</td> <td>Part B: Class 8,3 UN 2734</td> </tr> </table> </td> </tr> </table>		Dulux Protective Coatings a division of		<b>PACKAGING, TRANSPORT AND STORAGE</b>	DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	<table border="0"> <tr> <td>PACKAGING</td> <td>Available in 15 litre packs</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.61 kg/litre (Average of components)</td> </tr> <tr> <td>DA</td> <td>Part A: Class 3 UN 1263</td> </tr> <tr> <td>DD</td> <td>Part B: Class 8,3 UN 2734</td> </tr> </table>	PACKAGING	Available in 15 litre packs	TRANSPORTATION WEIGHT	1.61 kg/litre (Average of components)	DA	Part A: Class 3 UN 1263	DD	Part B: Class 8,3 UN 2734
Dulux Protective Coatings a division of		<b>PACKAGING, TRANSPORT AND STORAGE</b>													
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	<table border="0"> <tr> <td>PACKAGING</td> <td>Available in 15 litre packs</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.61 kg/litre (Average of components)</td> </tr> <tr> <td>DA</td> <td>Part A: Class 3 UN 1263</td> </tr> <tr> <td>DD</td> <td>Part B: Class 8,3 UN 2734</td> </tr> </table>	PACKAGING	Available in 15 litre packs	TRANSPORTATION WEIGHT	1.61 kg/litre (Average of components)	DA	Part A: Class 3 UN 1263	DD	Part B: Class 8,3 UN 2734					
PACKAGING	Available in 15 litre packs														
TRANSPORTATION WEIGHT	1.61 kg/litre (Average of components)														
DA	Part A: Class 3 UN 1263														
DD	Part B: Class 8,3 UN 2734														

Dulux, Duremax, Durepon and Zincode are registered trade marks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.