

LUXATHANE® DTM

Direct to Prepared Metal Polyurethane Finish

PC 401

- FEATURES**
- CONTAINS CORROSION INHIBITING PIGMENT ZINC PHOSPHATE
 - INCREASED PRODUCTIVITY, NO PRIMER REQUIRED IN MILD CORROSIVE CONDITIONS
 - VERY GOOD UV RESISTANCE AND GLOSS RETENTION
 - GOOD DRYING AND RECOAT PROPERTIES
 - TINTABLE – AVAILABLE IN OVER 2,500 COLOURS
 - GLOSS FINISH

USES LUXATHANE® DTM is a two-component acrylic polyurethane that incorporates the rust inhibitive pigment, zinc phosphate, allowing for direct application to abrasive blast or power tool cleaned steel. LUXATHANE® DTM delivers both corrosion protection and an attractive decorative gloss finish. The high build properties of LUXATHANE® DTM direct to metal surfaces, without the use of a primer, allows for the fast coating of steel that is subject to sheltered or mild (C1-C3) corrosive environments.

Typical areas of application of LUXATHANE® DTM include structural frames and trusses for factories and warehouses, farm and heavy engineering equipment.

LUXATHANE® Accelerator is available for use with Standard Hardener to promote faster drying.

SPECIFICATIONS

RESISTANCE GUIDE

WEATHERABILITY	Very good gloss and colour retention on exterior exposure	SOLVENTS	Unaffected by splash and spillage of common alcohols, aliphatic and aromatic hydrocarbons, esters and ketones
HEAT RESISTANCE	Up to 120°C dry heat	WATER	Excellent resistance to fresh and salt water but not suitable for immersion
SALTS	Unaffected by splash and spillage of most salt solutions	ALKALIS	Good resistance to splash and spillage of most common alkalis
ACIDS	Good resistance to splash and spillage of most common acids	ABRASION	Very good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	Two pack acrylic polyurethane coating		APPLICATION CONDITIONS			
FINISH	Gloss			Min	Max	
COLOUR	White and an extensive range of tinted colours		Air Temp.	10°C	40°C	
			Substrate Temp.	10°C	40°C	
			Relative Humidity	85%		
COMPONENTS	Two		COATING THICKNESS (MICRONS)			
VOLUME SOLIDS	55% (White)			Min	Max	Recommended
VOC LEVEL	<430 g/litre (White, untinted)		Wet film per coat (µm)	110	165	145
FLASH POINT	>23°C		Dry film per coat (µm)	60	90	80
POT LIFE	5 hours (4 litre kit, 25°C)					
MIXING RATIO V/V	Part A : 4	Part B : 1	SUITABLE SUBSTRATES	Abrasive blast cleaned, hand cleaned or power tool cleaned steel		
THINNER – BRUSH	965-63023	Urethane Thinner				
THINNER – SPRAY	965-63023	Urethane Thinner				
			PRIMERS	N/A		
			TOPCOATS	N/A		
			APPLICATION METHODS	Conventional, HVLP, airless spray or air assisted spray		
PRODUCT CODE	727-63313	White				
	727-39141	Golden Yellow				
	727-63001	Light Base				
	727-63003	Clear Base				
	976-H0165	Standard Hardener				
	976-H0229	Part C Accelerator				

DRYING CHARACTERISTICS AT 80 µm DRY FILM THICKNESS

					OVERCOAT	
Temperature	Humidity	Touch	Handle	Full Cure	Min	Max*
10° C	50%	75 Minutes	13 Hours	7 Days	13 Hours	Extended
15° C	50%	60 Minutes	10 Hours	7 Days	10 Hours	Extended
25° C	50%	30 Minutes	5 Hours	7 Days	5 Hours	Extended

These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE ASSUMING NO LOSSES

6.8 square metres per litre equals 80 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

LUXATHANE® DTM

STANDARD HARDENER WITH ACCELERATOR (PART C)

MIXING RATIO | PART C: 1 DOSE PER 4 LITRE KIT

COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	110	165	145
Dry film per coat (µm)	60	90	80

APPLICATION CONDITIONS

	Min	Max
Air Temperature	10°C	40°C
Substrate Surface Temperature	10°C	40°C
Relative Humidity		85%

SOLIDS BY VOLUME	54% (White)
VOC LEVEL	<440 g/L (White)
POT LIFE	5 Hours (4 Litre kit, 25°C)

DRYING CHARACTERISTICS AT 80 µm DRY FILM THICKNESS*

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT*	
					Min	Max
15° C	50%	50 minutes	6 Hours	7 Days	6 Hours	Extended
25° C	50%	25 minutes	4 Hours	7 Days	4 Hours	Extended

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE

with Accelerator
assuming no losses

6.7 square metres per litre equals 80 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

LUXATHANE® DTM

SURFACE PREPARATION	Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1 using Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's written instructions and all safety warnings. Abrasive blast clean to a minimum of AS1627.4 Class 2.5 with a blast profile of 40 – 70 microns. Remove all dust brushing or vacuum. Non-ferrous metals: Round off all sharp edges. Degrease in accordance with AS1627.1. Whip blast with fine non-metallic media to provide a key. Remove all dust with compressed air. Alternatively, degrease and abrade the surface with a non-metallic abrasive pad wetted with Gamlen CA 1 and water. Rinse thoroughly with fresh potable water.														
APPLICATION	Mix each can thoroughly using a power mixer until the contents are uniform. Ensure bases have been tinted to the correct colour before use. DULUX® ASSUMES NO RESPONSIBILITY FOR THE APPLICATION OF INCORRECT COLOUR. Mix the contents of both packs together thoroughly with a power mixer and let stand for 10 minutes. Box all containers before use to ensure colour consistency. Remix thoroughly before application.														
BRUSH/ROLLER	Suitable for small areas only. Thin with up to 100 ml/litre with Dulux® Urethane Thinner (965-63023) to aid application. When brushing and rolling additional coats may be required to attain the specified thickness.														
CONVENTIONAL SPRAY	Thin up to 150ml/litre with Dulux® Urethane Thinner (965-63023) to aid atomisation. Apply in multiple wet coats overlapping each pass 50% <table><tr><td>Typical Set-up</td><td>Graco AirPro:</td><td>1.8mm (239543)</td></tr><tr><td></td><td>Pressure at Triton 308:</td><td>65-100 kPa (10-15 p.s.i.)</td></tr><tr><td></td><td>Pressure at Gun:</td><td>385-420 kPa (55-60 p.s.i.)</td></tr><tr><td></td><td>HVLP</td><td>1.4 Fluid Tip Set</td></tr></table>			Typical Set-up	Graco AirPro:	1.8mm (239543)		Pressure at Triton 308:	65-100 kPa (10-15 p.s.i.)		Pressure at Gun:	385-420 kPa (55-60 p.s.i.)		HVLP	1.4 Fluid Tip Set
Typical Set-up	Graco AirPro:	1.8mm (239543)													
	Pressure at Triton 308:	65-100 kPa (10-15 p.s.i.)													
	Pressure at Gun:	385-420 kPa (55-60 p.s.i.)													
	HVLP	1.4 Fluid Tip Set													
AIRLESS SPRAY	Standard airless spray equipment such as a Graco Xtreme 30:1 with a fluid tip of 15 thou (0.38mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Thinning is not normally required but up to 100 ml/litre of Dulux® Urethane Thinner (965-63023) may be added to aid application.														
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Consultant for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the written consent of Dulux® Australia. Freshly mixed material must not be added to material that has been mixed for some time. The rate of cure is dependent upon temperature. Do not apply at temperatures below 5°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Ensure you read and understand the safety precautions on the Material Safety Data Sheets for the two components before using. The recommended thinner MUST be used as some solvents react with the isocyanate hardener seriously degrading the life of the coating. Under no circumstances should water or non-recommended thinner be allowed to contaminate the product. In hot weather use DUTHIN® 040 (965-42166) to improve flow and to reduce dry spray. Use of Part C Luxathane® Accelerator may result in different gloss level and appearance when compared with result without Part C Luxathane® Accelerator. Use only within the allowable temperature ranges quoted above.														
CLEAN UP	Clean all equipment with Dulux® Urethane Thinner (965-63023) immediately after use.														
OVERCOATING	Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating.														
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au														
STORAGE	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in a dry, well-ventilated area away from sources of heat or ignition. Keep containers closed at all times. Avoid moisture contamination.														
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 must be worn while handling and using. Always wash hands before smoking, eating, drinking or using the toilet. Isocyanate in the hardener reacts with water to produce gas. If a closed container shows signs of internal pressure, cover it completely with a cloth and remove the lid slowly to prevent splashing or violent expulsion of the lid.														
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. When spraying, wear a positive-pressure, air-supplied respirator. Users must comply with the provisions of the respective State Spray Painting Regulations at all times.														
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO ₂ or dry chemical powder. On burning will emit toxic fumes.														
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.														

COMPANY INFORMATION		PACKAGING, TRANSPORT AND STORAGE	
Dulux Protective Coatings a division of		PACKAGING	Available in 4 litre packs
DuluxGroup (Australia) Pty Ltd	DuluxGroup (New Zealand) Pty Ltd	TRANSPORTATION WEIGHT	1.28 kg/litre (Average of components)
1956 Dandenong Road, Clayton 3168	150 Hutt Park Road, Lower Hutt, NZ	DANGEROUS GOODS	Part A: Class 3 UN 1263
A.B.N. 67 000 049 427	A.B.N. 55 133 404 118		Part B: Class 3 UN 1263

Dulux, Duthin® and Luxathane are registered trade marks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.