

LUXAFLOOR® WB SEALER

Water Based Acrylic Concrete Sealer

PC 230

- FEATURES**
- LOW ODOUR – WATERBASED & LOW VOC
 - CLEAR COATING FOR INTERIOR & EXTERIOR APPLICATION - UV RESISTANT
 - SEAL LINE MARKING – COMPATIBLE WITH DULUX ROADMASTER A1 & ROADMASTER WB2
 - ACHIEVE THREE COATS IN ONE DAY – ONE HOUR RECOAT TIME

USES LUXAFLOOR® WB SEALER is a one pack water based acrylic sealer, ideal for sealing dust & dirt and sealing lines on concrete where low odour is required. This product is compatible with Dulux® line marking products Roadmaster® A1 and Roadmaster® WB2.

LUXAFLOOR® WB SEALER is suitable for car parks, warehouses, garages, workshops, concrete driveways etc.

SPECIFICATIONS
RESISTANCE GUIDE

WEATHERABILITY	Non-yellowing and resists UV on exterior exposure	SOLVENTS	Resists Petrol and has limited resistance to Diesel. Strong solvents are liable to attack the coating
HEAT RESISTANCE	Up to 65°C dry heat	WATER	Excellent resistance to rain and condensation. Do not expose to permanently damp conditions or immersion
SALTS	Good resistance to neutral and alkali salts	ALKALIS	Good resistance to splash and spillage of most common alkalis
ACIDS	Good resistance to splash and spillage of mild acids	ABRASION	Good

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	One pack acrylic sealer	APPLICATION CONDITIONS			
FINISH	Gloss (Dependant on number of coats)		Min	Max	
COLOUR	Clear Colourless	Air Temp.	10°C	35°C	
		Substrate Temp.	10°C	35°C	
		Relative Humidity		85%	
		Concrete Moisture		<6%	
COMPONENTS	One	COATING THICKNESS (MICRONS)			
VOLUME SOLIDS	16%		Min	Max	Recommended
VOC LEVEL	<34g/L	Wet film per coat (µm)	65	130	95
FLASH POINT	Not applicable	Dry film per coat (µm)	10	20	15
POT LIFE	Not applicable	SUITABLE SUBSTRATES	Clean concrete and other cementitious substrates.		
MIXING RATIO V/V	Not applicable	PRIMERS	Suitable for application over Dulux Roadmaster A1 and Roadmaster WB2.		
THINNER	Do not thin	TOPCOATS	LUXAFLOOR® WB SEALER		
PRODUCT CODE	599-H0251 LUXAFLOOR® WB SEALER	APPLICATION METHODS	Brush, roller, conventional, airless spray or air assisted spray		

DRYING CHARACTERISTICS AT 15 µm DRY FILM THICKNESS*

Temperature	Humidity	Light traffic	Full Cure	OVERCOAT	
				Min	Max
10° C	50%	4 Hours	7 Days	4 Hours ¹	Extended ²
15° C	50%	2 Hours	7 Days	2 Hours ¹	Extended ²
25° C	50%	1 Hour	7 Days	1 Hours ¹	Extended ²

*These figures are a guide only, as ventilation, film thickness, humidity, and other factors will influence the rate of drying.

¹Luxafloor® Sealer will be suitable for over coating once it is dry and changes from cloudy to clear. Good ventilation will significantly assist in drying. The coating will take longest to dry where it pools inside cracks in the concrete. As a rule, the first coat will dry faster than the subsequent coats.

² Extended max overcoat – This product is readily recoatable with itself as long as the surface to be coated is clean, dry and free from contaminants. Limitations to recoating will be affected by weathering and contamination and will depend on the service environment.

SPREADING RATE 10.6 square metres per litre equals 15 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

LUXAFLOOR® WB SEALER

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
UNCOATED CONCRETE	Exterior/Interior	Remove release agents and other surface contaminants	1 st Coat Luxafloor® WB Sealer	15 µm
			2 nd Coat Luxafloor® WB Sealer	15 µm
			3 rd Coat ² Luxafloor® WB Sealer	15 µm
ROADMASTER A1	Exterior/Interior	Allow Roadmaster A1 to cure for 3 hours before sealing. Otherwise the coating may fry.	1 st Coat ¹ Luxafloor® WB Sealer	15 µm
ROADMASTER WB2	Exterior/Interior	Allow Roadmaster WB2 to cure for 3 hours before sealing. Otherwise the coating may fry.	1 st Coat ¹ Luxafloor® WB Sealer	15 µm

¹Multiple coats may be required to achieve a gloss finish over road marking.

²Additional coats may be required to seal especially porous concrete.

SURFACE PREPARATION	Luxafloor® WB SEALER will not properly adhere to surfaces that have been treated with curing compounds or bond breakers; these treatments must be completely removed before application. Concrete must be at least 28 days old before coating. Remove curing compounds, oil, grease and other oily contaminants. The prepared surface should readily absorb water and show no signs of any water beading. Diamond grind, track or light shot-blast concrete floors to remove laitance and to provide a suitable profile. High pressure washing may be suitable. Remove all dust by vacuum cleaning. Check moisture content of the floor prior to painting.			
APPLICATION BRUSH/ROLLER	Suitable for brush and roller application. Use a 10mm or 12mm synthetic woven nap sleeve. Do not use medium or long nap roller sleeves. Roller marks or "tracks" may appear whilst the coating is being applied, but these will dry out. When brushing and rolling, additional coats may be required to attain the specified thickness.			
APPLICATION SPRAY APPLICATION	Airless Spray			
	Tip Orifice	Atomising Pressure	Mat'l Hose ID	Pump Manifold Filter
	0.010" – 0.015" (254 - 381 microns)	1,100 – 1500 psi (75.84 – 103.42 bar)	1/4" or 3/8" (6 or 10 mm)	100 mesh (149 microns)
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Ensure that you read and understand the safety precautions on the relevant Safety Data Sheets before using. The surface to be coated must be totally free of contaminants. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. The rate of cure is dependent upon temperature. Where application conditions are outside the parameters stated in this Product Data Sheet, or where any variation to the recommendations are sought, contact your Dulux® technical representative for written specifications prior to application. Note – Rubber-tyred vehicles, particularly those using new high-performance car tyres, may cause yellowing or staining on floor coatings. The rubber can contain materials that will migrate into the surface coating and cause this effect. This is dependent on the composition and age of the tyre and may affect all coatings to a greater or lesser extent. Refer to our tech note (https://www.duluxprotectivecoatings.com.au/media/1542/139-concrete-floors-tyre-staining.pdf) to find out more about tyre staining and how it can be managed. Dulux Protective Coatings cannot guarantee the resistance of our coatings to this effect and will take no responsibility where tyre staining occurs.			
CLEAN UP	Clean all equipment with potable water immediately after use.			
OVERCOATING	Degrease with Gamlen CA 1 according to the manufacturer's written instructions and all safety warnings. As a general rule, do not overcoat this material with a two-pack coating. When overcoating, test the adhesion of the existing coating by standard cross hatch adhesion test. If the coating fails, remove it. If coating inside, fill any cracks or defects in the concrete with an appropriate filler and spot prime bare areas with the specified floor coating. Mechanically grind the existing coating to remove any gloss and create a good key for the new coating. Vacuum clean to remove all dust.			
SAFETY PRECAUTIONS	Read Technical Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au			
STORAGE	Store in a cool, dry, well-ventilated place and out of direct sunlight. Store away from foodstuffs. Store away from incompatible materials described in Section 10 of the Safety data sheet. Store away from sources of heat and/or ignition. Keep container standing upright. Keep containers closed when not in use - check regularly for leaks.			
HANDLING	Avoid eye contact and repeated or prolonged skin contact. Avoid inhalation of vapour, mist or aerosols.			
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. Users must comply with the provisions of the respective Local Spray Painting Regulations at all times.			
FLAMMABILITY	This product is not flammable. On burning will emit toxic fumes.			

COMPANY INFORMATION

Dulux Protective Coatings a division of
DuluxGroup (Australia) Pty Ltd
1956 Dandenong Road, Clayton 3168
A.B.N. 67 000 049 427

DuluxGroup (New Zealand) Pty Ltd
150 Hutt Park Road, Lower Hutt, NZ
A.B.N. 55 133 404 118

PACKAGING, TRANSPORT AND STORAGE

PACKAGING Available in 15 litre packs
TRANSPORTATION WEIGHT 1.08kg/L
DANGEROUS GOODS Non-dangerous goods

Dulux and Luxafloor are registered trademarks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.

LUXAFLOOR® WB SEALER

CHEMICAL RESISTANCE GUIDE

Chemical	Splash & spill (24hr removal)	Chemical	Splash & spill (24hr removal)
Alkali		Solvents and Fluids	
10% Sodium Hydroxide	Excellent	Engine Oil 5W40	Excellent
		Engine Oil 20W50	Excellent
Acid		Petrol	Excellent
10% Sulphuric acid	Excellent	Diesel	Good (S)
		Brake Fluid DOT3	Good (S)
		Brake Fluid DOT4	Good (S)
		Skydrol	Not recommended
		Xylene	Not recommended

*S = Concrete staining observed

The above chart relates to a coating system of three coats of Luxafloor® Sealer allowed to cure for 7 days.