

LUXATHANE® MPX

Matt Finish Recoatable Classic Polyurethane Topcoat

PC 400

- FEATURES**
- SMOOTH MATT FINISH
 - GOOD UV AND GLOSS RETENTION
 - EXCELLENT DRYING AND HANDLE PROPERTIES
 - LONG TERM RECOATABILITY

USES Luxathane® MPX is a matt finish, two-component acrylic polyurethane. It is designed for use in areas where an aesthetically pleasing, matt finish is desired. Luxathane® MPX is formulated for use in commercial and industrial environments where extended service periods are required. The matt finish is suitable for steelwork and facades of architectural and commercial projects, such as retail complexes and high-rise offices and apartments.

Luxathane® MPX can be used directly over Dulux® Protective Coatings range of primers and intermediate coatings.

SPECIFICATIONS

RESISTANCE GUIDE

WEATHERABILITY	Very good gloss and colour retention on exterior exposure	SOLVENTS	Suitable for occasional splash and spillage of common solvents
HEAT RESISTANCE	Up to 120°C dry heat	WATER	Suitable for exposure to occasional splash and spillage of fresh and salt water but not suitable for immersion
SALTS	Unaffected by occasional splash and spillage of most salt solutions	ALKALIS	Suitable for occasional splash and spillage of most common alkalis
ACIDS	Suitable for occasional splash and spillage exposure to some acids	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	Two pack acrylic polyurethane coating		APPLICATION CONDITIONS			
FINISH	Matt, 2-5 gloss at 60°			Min	Max	
COLOUR	White, Black, and a full range of tinted colours		Air Temp.	10°C	40°C	
COMPONENTS	Two		Substrate Temp.	10°C	40°C	
VOLUME SOLIDS	47 ± 2%		Relative Humidity		85%	
VOC LEVEL	<540 g/L		COATING THICKNESS (MICRONS)			
FLASH POINT	>23°C			Min	Max	Recommended
POT LIFE	4 hours (4 litre kit, 25°C)		Wet film per coat (µm)	110	150	130
MIXING RATIO V/V	Part A : 4	Part B : 1	Dry film per coat (µm)	50	70	60
THINNER	965-63023	Dulux® Urethane Thinner	SUITABLE SUBSTRATES	Suitably primed substrates, including steel, aluminium, zinc coated steel, and concrete.		
THINNER -HOT WEATHER	920-89963	Duthin® 511 X-Slow Thinner	PRIMERS	Specified Dulux® Protective Coatings range of primers and intermediates.		
PRODUCT CODE	749-63001	Light Base	APPLICATION METHODS	Airless and conventional spray		
	749-63002	Deep Base				
	749-63003	Clear Base				
	749-00070	Black				
	749-63313	White				
	976-H0237	Standard Hardener				
	976-H0229	Part C Accelerator				

DRYING CHARACTERISTICS AT 60 µm DRY FILM THICKNESS*

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT*	
					Min	Max
10° C	50%	90 Minutes	9 Hours	7 Days	9 Hours	Extended
15° C	50%	60 minutes	6 Hours	7 Days	6 Hours	Extended
25° C	50%	30 minutes	3 Hours	7 Days	3 Hours	Extended

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE

ASSUMING NO LOSSES

7.8 square metres per litre equals 60 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as colour, application method, ambient conditions and surface porosity and roughness.

LUXATHANE® MPX

STANDARD HARDENER WITH ACCELERATOR (PART C)

MIXING RATIO | Part C: 1 dose per 4 litre mixed kit

COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	110	155	130
Dry film per coat (µm)	50	70	60

APPLICATION CONDITIONS

	Min	Max
Air Temperature	10°C	30°C
Substrate Surface Temperature	10°C	30°C
Relative Humidity		85%

SOLIDS BY VOLUME	46 ± 2 %
VOC LEVEL	<500 g/L (White)
POT LIFE	3 hours (4 litre kit, 25°C)

DRYING CHARACTERISTICS AT 60 µm DRY FILM THICKNESS* (ACCELERATOR)

OVERCOAT*

Temperature	Humidity	Touch	Handle	Full Cure	Min	Max
10° C	50%	75 Minutes	6 Hours	7 Days	6 Hours	Extended
15° C	50%	50 Minutes	4 Hours	7 Days	4 Hours	Extended
25° C	50%	25 Minutes	3 Hours	7 Days	3 Hours	Extended

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE 7.7 square metres per litre equals 60 µm dry film thickness

with Cold Cure Hardener
assuming no losses

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
STEEL – NEW	Medium–high corrosivity (AS2312.1 Cat C4) System PUR4	Abrasive blast AS1627.4 Class 2.5	1 st Coat Zincanode® 402	75 µm
			2 nd Coat Duremax® GPE	125 µm
			3 rd Coat Luxathane® MPX	60 µm
STEEL – NEW	Low corrosivity (AS2312.1 Cat C2) System PUR2	Abrasive blast AS1627.4 Class 2.5	1 st Coat Durepon® EZP 2 nd Coat Luxathane® MPX	75 µm 60 µm
STEEL – NEW OR MAINTENANCE	Low corrosivity (AS2312.1 Cat C2) System PUR1	Abrasive blast AS1627.4 Class 2 or power tool clean AS1627.2 St 3	1 st Coat Durebild® STE 2 nd Coat Luxathane® MPX	125 µm 60 µm
CONCRETE	Exterior/Interior	Remove release agents and other surface contaminants	1 st Coat Durebild® STE 2 nd Coat Luxathane® MPX 3 rd Coat Luxathane® MPX	125 µm 60 µm 60 µm

NOTE: If applied by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity.

LUXATHANE® MPX

SURFACE PREPARATION

Specifiers should follow the surface preparation guidelines from the data sheet for the primer or first coat selected. The surface must be clean, sound and free from moisture, grease, oil, dirt, rust, loose paint, and other contaminants. If application of the second coat has exceeded the recoat window of the first coat (refer to data sheet) then the entire surface MUST be abraded to maximise adhesion.

APPLICATION

Premix Part A thoroughly using a power mixer until the contents are uniform. Ensure bases have been tinted to the correct colour before use. DULUX® ASSUMES NO RESPONSIBILITY FOR THE APPLICATION OF INCORRECT COLOUR. Mix the contents of both packs together thoroughly for a minimum of 2 minutes using a power mixer and a clean helical mixing blade. Box all containers before use to ensure colour consistency. Remix thoroughly before application.

APPLICATION EQUIPMENT	Airless Spray: Graco e-Xtreme EX35 or equivalent Thinning is not normally required but up to 50 ml/litre or 5% by volume of Dulux® Urethane Thinner (965-63023) or Duthin® 511 X-Slow Thinner (920-89963) may be added to aid application. Apply in multiple wet coats overlapping each pass 50%.						
	Tip Orifice	Atomising Pressure		Mat'l Hose ID		Pump Manifold Filter	
	0.011" – 0.015" (280 - 380 microns)	2,400 – 3,000 psi (150 – 207 bar)		3/8" (9.5 mm)		100 mesh (149 microns)	
	NOTE: A 0.9 metre x 1/4" (6.35mm) whip hose was used at the end of the material hose.						
	Air Spray: Graco Triton 308 or equivalent. Thin 50ml/litre or 5% by volume of Dulux® Urethane Thinner (965-63023) or Dulux® Duthin® 511 X-Slow Thinner (920-89963) maybe added to aid in application. Apply in multiple wet coats overlapping each pass 50%.						
	Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomising Pressure	Pot Pressure
	Graco Air Pro or Equivalent	2.2 mm (0.086)	Graco 192318	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	40 to 50PSI (2.76 – 3.45 Bar)	15 to 25PSI (1.03 – 1.72 Bar)
	NOTE: Low temperatures and/or long hose lengths require higher material pressure.						
	Roller and Brush: Thin up to 10% to 15% Dulux® Urethane Thinner (965-63023) or Duthin® 511 X-Slow Thinner (920-89963) to aid application if required. Recommended for small touch up areas only. Use synthetic woven nap cover. Do not use long nap covers. A thin nap roller cover such a 6mm is recommended. For brushes use a high quality natural or synthetic bristle brushes. Note: Two or more coats may be required to obtain recommended film thicknesses.						
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Ensure that you read and understand the safety precautions on the relevant Safety Data Sheets before using. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. The rate of cure is dependent upon temperature. Where application conditions are outside the parameters stated in this Product Data Sheet, or where any variation to the recommendations are sought, contact your Dulux® Protective Coatings Consultant for written specifications prior to application. Freshly mixed material must not be added to previously mixed material. The recommended thinner MUST be used as some solvents react with the isocyanate hardener seriously degrading the life of the coating. Under no circumstances should water or non-specified thinner be allowed to contaminate the product. To minimise variations in gloss and appearance on an area to be coated, ensure that the Accelerator is used in all kits or not at all, ie do not paint half the area with the Accelerator and half without, as this may result in a slight difference in gloss. The Accelerator will speed up handle and dry times when used within the allowable temperature ranges quoted above. However, if lower than recommended application and substrate temperatures occur during curing, solvent entrapment and low gloss may occur due to the effects of condensation/dew. In hot weather, use Duthin® 511 X-Slow Thinner (920-89963) to improve flow and to reduce dry spray.						
CLEAN UP	Clean all equipment with Dulux® Urethane Thinner (965-63023) or Duthin® 511 X-Slow Thinner (920-89963) immediately after use.						
OVERCOATING	Exiting coatings must be assessed for suitability in terms of their condition, adhesion to substrate and ability to accept additional coats. Appropriate tests are the latest versions of SSPC TU No.3, ASTM D 5064, and ASTM D 5065. Consult your local Dulux® Protective Coatings Consultant for specific surface preparation and coating system recommendations..						
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au						
STORAGE	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.						
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 must be worn while handling and using. Always wash hands before smoking, eating, drinking or using the toilet. Gas is evolved when isocyanate in the hardener reacts with water. If a closed container, of either hardener or catalysed paint, shows signs of internal pressure, cover it completely with a cloth and remove the lid slowly to prevent splashing or violent expulsion of the lid.						
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. When spraying, wear a positive-pressure, air-supplied respirator. Users must comply with the provisions of the respective State Spray Painting Regulations at all times.						
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO2 or dry chemical powder. On burning will emit toxic fumes.						
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.						
COMPANY INFORMATION				PACKAGING, TRANSPORT AND STORAGE			
Dulux Protective Coatings a division of				PACKAGING Available in 4 litre packs			
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427		DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118		TRANSPORTATION WEIGHT 1.24 kg/litre (Average of components)		DANGEROUS GOODS Part A: Class 3 UN 1263 Part B: Class 3 UN 1866	
Dulux, Duthin, Durebild, Durepon, Duremax, Luxathane, Luxepoxy and Zincanode are registered trademarks of DuluxGroup (Australia) Pty Ltd.							
Any advice, recommendation, information, assistance or service provided by Dulux® Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux® to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux® is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux® by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.							