

LUXAFLOOR® EXPRESS PRIMER

Two Pack Epoxy Primer

PC704

- FEATURES**
- RETURN TO SERVICE FAST WHEN TOPCOATED WITH LUXAFLOOR® FCF
 - SAME DAY RECOATABILITY POSSIBLE
 - READY FOR USE, NO THINNING REQUIRED
 - EXCELLENT ADHESION WITH LUXAFLOOR® FCF

USES LUXAFLOOR® EXPRESS PRIMER is a two-pack express epoxy primer for concrete floors. This product is ideal to use in conjunction with any pigmented LUXAFLOOR® flooring topcoats to help return the floor to service faster. LUXAFLOOR® EXPRESS PRIMER is suitable for use in commercial and industrial environments such as warehouses, factories, retail spaces, car parks as a first coat before being topcoated.

RESISTANCE GUIDE

WEATHERABILITY	Will yellow with time. Will chalk on exposure to UV. Neither yellowing nor chalking detracts from the protective properties of the coating. Use a weatherable topcoat if appearance is important.	SOLVENTS	Resists splash and spillage of most hydrocarbons, refined petroleum products and most common alcohols when topcoated.
HEAT RESISTANCE	Up to 120°C dry heat	WATER	Excellent resistance to fresh and salt water but not suitable for immersion.
SALTS	Unaffected by splash and spillage of neutral and alkaline salt solutions when topcoated.	ALKALIS	Good resistance to splash and spillage of most common alkalis when topcoated.
ACIDS	Good resistance to splash and spillage of most acids when topcoated.	ABRASION	Excellent when fully cured and topcoated.

TYPICAL PROPERTIES AND APPLICATION DATA (STANDARD HARDENER)

CLASSIFICATION	Two Pack Epoxy Primer		APPLICATION CONDITIONS			
FINISH	Low Sheen			Min	Max	
COLOUR	Pale Grey		Air Temp.	5°C	40°C	
COMPONENTS	Two		Substrate Temp.	5°C	40°C	
VOLUME SOLIDS	65%		Relative Humidity	85%		
VOC LEVEL	<285 g/L		Concrete Moisture*	<6%		
FLASH POINT	>23°C		COATING THICKNESS (MICRONS)			
POT LIFE	1 hour (10 litre kit, 25°C)			Min	Max	Recommended
MIXING RATIO V/V	Part A : 4	Part B : 1	Wet film per coat (µm)	115	230	154
THINNER	920-08925	Dulux® Epoxy Thinner	Dry film per coat (µm)	75	150	100
PRODUCT CODE	780-H0252	LUXAFLOOR® EXPRESS PRIMER PT A	SUITABLE SUBSTRATES	Prepared concrete		
	976-H0253	LUXAFLOOR® EXPRESS PRIMER PT B	TOPCOATS	Dulux® Luxafloor® pigmented two pack topcoats.		
			APPLICATION METHODS	Brush and roller		

*See page 2 for more information about concrete moisture

DRYING CHARACTERISTICS AT 100 µm DRY FILM THICKNESS* (STANDARD HARDENER)

Temperature	Humidity	Touch	Light traffic	Full Cure	OVERCOAT	
					Min	Max ¹
5° C	50%	8 Hours	12 Hours	7 Days	12 Hours	48 Hours
10° C	50%	6 Hours	9 Hours	7 Days	9 Hours	48 Hours
15° C	50%	4 Hours	6 Hours	7 Days	6 Hours	48 Hours
25° C	50%	2 Hours	3 Hours	7 Days	3 Hours	24 Hours
35° C	50%	1 Hour	1.5 Hours	7 Days	1.5 Hours	24 Hours

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹If the maximum overcoat interval is exceeded then the surface **MUST** be abraded to ensure maximum intercoat adhesion.

SPREADING RATE

with Standard Hardener assuming no losses

6.5 square metres per litre equals 100 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

LUXAFLOOR® EXPRESS PRIMER

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
CONCRETE	Light Commercial Exterior/Interior	Remove curing agents and other surface contaminants. Diamond grind or track blast to provide a good key.	REPAIRS 1 st Coat Luxafloor® Express Primer 2 nd Coat Luxafloor® FCF	N/A 100 µm 75 µm
CONCRETE	Industrial Exterior/Interior	Remove curing agents and other surface contaminants. Diamond grind or track blast to provide a good key.	REPAIRS 1 st Coat Luxafloor® Filler 2 nd Coat Luxafloor® Express Primer 3 rd Coat Luxafloor® FCF	N/A 100 µm 75 µm 75 µm
CONCRETE	Non Slip Exterior/Interior	Remove curing agents and other surface contaminants. Diamond grind or track blast to provide a good key.	REPAIRS 1 st Coat Luxafloor® Filler 2 nd Coat Luxafloor® Express Primer 3 rd Coat Luxafloor® FCF with Luxafloor® Broadcast Aggregate No 36	N/A 100 µm 75 µm 75 µm
CONCRETE	High Gloss Interior	Remove curing agents and other surface contaminants. Diamond grind or track blast to provide a good key.	REPAIRS 1 st Coat Luxafloor® Filler 2 nd Coat Luxafloor® Express Primer 3 rd Coat Luxafloor® HSG	N/A 100 µm 100 µm 100 µm
CONCRETE	Gloss Interior/Exterior	Remove curing agents and other surface contaminants. Diamond grind or track blast to provide a good key.	REPAIRS 1 st Coat Luxafloor® Filler 2 nd Coat Luxafloor® Express Primer Luxafloor® PTX	N/A 100 µm 100 µm

NOTE: If application is by brush or roller, additional coats may be necessary to achieve the minimum DFT and full opacity. A 12mm or higher nap roller is recommended.

SURFACE PREPARATION	<p>Concrete: Concrete must be at least 28 days old before coating. Remove curing compounds, oil, grease and other oily contaminants. Diamond grind, track blast or light shot-blast concrete floors to remove laitance and to provide a suitable profile. Remove all dust by vacuum cleaning. Fill any large cracks or voids with Luxafloor® Filler. Check moisture content of the floor prior to painting*.</p> <p>*Allow new concrete to cure a minimum of 28 days at 24°C. To minimise the risk of moisture interference, Dulux recommends the following two tests be performed prior to coating – ASTM F2659 – 10 “Standard Guide for Preliminary Evaluation of Comparative Moisture Condition of Concrete, Gypsum Cement and Other Floor Slabs and Screeds Using a Non-Destructive Electronic Moisture Meter”(moisture content not to exceed 6%) and ASTM D 4263 “Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method” (no visible moisture present). If there is any concern about moisture problems with the concrete slab, or for projects greater than 500m², at least one of the following more accurate quantitative test methods should be used - ASTM F 1869 “Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride” (moisture vapor transmission should not exceed 1.4 kilograms (3 pounds) per 93 square metres (1,000 square feet) in a 24 hour period), ASTM F 2170 “Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes” (as referred to in AS 1884-2012, relative humidity should be less than 75%) Note: The testing listed above cannot guarantee avoidance of future moisture related problems particularly with existing concrete slabs. This is especially true if the use of an under-slab moisture vapor barrier cannot be confirmed or concrete contamination from oils, chemical spills, unreacted silicates, chlorides or Alkali Silica Reaction (ASR) is suspected.</p> <p>Concrete with Existing Coating: Refer to Overcoating guidance below.</p>
APPLICATION	Mix each can thoroughly using a power mixer until the contents are uniform. Mix the contents of both pails together thoroughly using a power mixer for a minimum of 2-3 minutes.
BRUSH/ROLLER	Use a 12mm or higher nap roller to achieve the specified thickness. Higher nap rollers are recommended to assist application on rough surfaces. Thinning is not normally required, however a small amount (10% or less by volume) of Dulux® Epoxy Thinner (920- 08925) can be added.
PRECAUTIONS	<p>This is an industrial product designed for use by experienced Protective Coating applicators. Ensure that you read and understand the safety precautions on the relevant Safety Data Sheets before using. Do not apply at temperatures below 5°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. The rate of cure is dependent upon temperature. Where application conditions are outside the parameters stated in this Technical Data Sheet, or where any variation to the recommendations are sought, contact your Dulux® Consultant for written specifications prior to application. Clear coatings are not recommended over Luxafloor® Express Primer. Ensure that Luxafloor® Express Primer is topcoated within 24 hours when used with Luxafloor® FCF. Freshly mixed material must not be added to previously mixed material.</p> <p>Note – Rubber-tyred vehicles, particularly those using new high-performance car tyres, may cause yellowing or staining on floor coatings. The rubber can contain materials that will migrate into the surface coating and cause this effect. This is dependent on the composition and age of the tyre and may affect all coatings to a greater or lesser extent. Refer to our tech note (https://www.duluxprotectivecoatings.com.au/media/1542/139-concrete-floors-tyre-staining.pdf) to find out more about tyre staining and how it can be managed. Dulux Protective Coatings</p>
CLEAN UP	Clean all equipment with Dulux Epoxy Thinner (920-08925).

LUXAFLOOR® EXPRESS PRIMER

OVERCOATING	Overcoat evaluations must be performed to ensure compatibility between the aged existing coating system and the proposed new coating system. Additionally, it is imperative to understand if an acceptable level of adhesion can be achieved between the two systems. Evaluations which must occur include a visual and physical inspection of the existing coating system and representative test patch evaluations of the new system over the existing aged coating system. Inclusive of the test patch evaluation requires adhesion testing by AS 3894.9, "Determination of Adhesion", Method A, "Knife Test" and/or Method C, "Pull Off Test". An acceptable result for Method A would be a rating of 2 or better. An acceptable result for Method C would be cohesive failure of the substrate. If the tensile strength of the coating is less than the tensile strength of the substrate, the coating system should be considered not suitable for coating over. Typical cohesive failure of concrete is in the range of 1.4 to 2.8 MPa. These evaluations should be accomplished in conjunction with your local Dulux PC Representative. If logistically not possible, contact your local Dulux PC Representative and/or Dulux PC Technical Services to discuss what these evaluations should consist of, and what a successful outcome would look like for a proposed overcoat system.												
SAFETY PRECAUTIONS	Read Technical Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEETS are available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au												
STORAGE	Store in a cool, dry, well-ventilated place and out of direct sunlight. Store away from foodstuffs. Store away from oxides of carbon and nitrogen, oxidising agents, smoke and other toxic fumes. Store away from sources of heat and/or ignition. Store locked up. Keep container standing upright. Keep containers closed when not in use - check regularly for leaks.												
HANDLING	Avoid eye contact and skin contact. Avoid inhalation of vapour, mist or aerosols.												
USING	Use with good ventilation and avoid inhalation of fumes. Wear safety shoes, overalls, gloves, chemical goggles, respirator. Use with adequate ventilation. If inhalation risk exists wear organic vapour/particulate respirator meeting the requirements of AS/NZS 1715 and AS/NZS 1716.												
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE . If material is involved in a fire use alcohol resistant foam or dry agent (carbon dioxide, dry chemical powder).												
COMPANY INFORMATION													
<table border="0"> <tr> <td>Dulux Protective Coatings a division of</td> <td></td> <td>PACKAGING, TRANSPORT AND STORAGE</td> </tr> <tr> <td>DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427</td> <td>DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118</td> <td> <table border="0"> <tr> <td>PACKAGING</td> <td>Available in 10 litre kits</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.626 kg/litre (Average of components)</td> </tr> <tr> <td>DANGEROUS GOODS</td> <td>Part A: Class 3 UN 1263 Part B: Class 8 UN 2734</td> </tr> </table> </td> </tr> </table>		Dulux Protective Coatings a division of		PACKAGING, TRANSPORT AND STORAGE	DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	<table border="0"> <tr> <td>PACKAGING</td> <td>Available in 10 litre kits</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.626 kg/litre (Average of components)</td> </tr> <tr> <td>DANGEROUS GOODS</td> <td>Part A: Class 3 UN 1263 Part B: Class 8 UN 2734</td> </tr> </table>	PACKAGING	Available in 10 litre kits	TRANSPORTATION WEIGHT	1.626 kg/litre (Average of components)	DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 8 UN 2734
Dulux Protective Coatings a division of		PACKAGING, TRANSPORT AND STORAGE											
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	<table border="0"> <tr> <td>PACKAGING</td> <td>Available in 10 litre kits</td> </tr> <tr> <td>TRANSPORTATION WEIGHT</td> <td>1.626 kg/litre (Average of components)</td> </tr> <tr> <td>DANGEROUS GOODS</td> <td>Part A: Class 3 UN 1263 Part B: Class 8 UN 2734</td> </tr> </table>	PACKAGING	Available in 10 litre kits	TRANSPORTATION WEIGHT	1.626 kg/litre (Average of components)	DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 8 UN 2734					
PACKAGING	Available in 10 litre kits												
TRANSPORTATION WEIGHT	1.626 kg/litre (Average of components)												
DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 8 UN 2734												

©Dulux and Luxafloor, are registered trademarks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.