

DUREPON® EZP

Two Pack Epoxy Zinc Phosphate Primer

PC 209

- FEATURES**
- INHIBITIVE EPOXY PRIMER FOR STEEL AND OTHER PREPARED SURFACES
 - SMOOTH FINISH
 - ANTI-CORROSIVE PIGMENTATION
 - GOOD CHEMICAL AND SOLVENT RESISTANCE
 - QUICKTURN™ FAST CURE HARDENER AVAILABLE

USES DUREPON® EZP is a two pack epoxy primer that is enhanced with zinc phosphate pigment for inhibitive corrosion protection on mild steel. It is suitable as a primer for steelwork in for a wide range of applications including commercial construction, manufacturing & chemical plants, power generation and sporting facilities.

DUREPON® EZP QUICKTURN™ hardener for faster overcoat time in standard conditions. It also acts as a cold cure hardener for cooler climates, curing down to 5°C (standard hardener limited to above 10°C).

DUREPON® EZP can be overcoated with epoxy, polyurethane or acrylic finishes depending upon the end requirements.

SPECIFICATIONS AS/NZS 3750.13 Type 2

RESISTANCE GUIDE

WEATHERABILITY	Will yellow with time. Will chalk on exterior exposure. Neither yellowing nor chalking detracts from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	SOLVENTS	Resists splash and spillage of most hydrocarbon solvents, refined petroleum products and most common alcohols
HEAT RESISTANCE	Up to 120°C dry heat	WATER	Excellent resistance to fresh and salt water. Not suitable for immersion.
SALTS	Unaffected by splash and spillage of neutral and alkaline salt solutions	ALKALIS	Excellent resistance to splash and spillage of most common alkalis
ACIDS	Suitable for splash and spillage of weak acids	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA (STANDARD HARDENER)

CLASSIFICATION	Epoxy zinc phosphate primer				APPLICATION CONDITIONS					
FINISH	Low Sheen				Air Temp. Substrate Temp. Relative Humidity	Min	Max			
COLOUR	Grey					10°C	40°C			
						10°C	40°C			
							85%			
COMPONENTS	Two									
VOLUME SOLIDS	52.8%				COATING THICKNESS (MICRONS)					
VOC LEVEL	<470 g/L					Min	Max	Recommended		
FLASH POINT	>23°C				Wet film per coat (µm)	95	170	140		
POT LIFE	3-4 hours (4 litre kit, 25°C)				Dry film per coat (µm)	50	90	75		
MIXING RATIO V/V	Part A : 3	Part B : 1								
THINNER	920-08925	Dulux® Epoxy Thinner			SUITABLE SUBSTRATES	Abrasive blast-cleaned steel				
	920-81942	Dulux® Duthin®	450	Cold						
		Weather Thinner								
PRODUCT CODE	410-H0154	Grey				PRIMERS	Not applicable			
	976-H0155	Standard Hardener								
	976-H0203	Quickturn™ Hardener				TOPCOATS	Single and two pack Dulux® products			
						APPLICATION METHODS	Brush, roller, conventional, airless spray or air-assisted spray.			

DRYING CHARACTERISTICS AT 75 µm DRY FILM THICKNESS* (STANDARD HARDENER)

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max ¹
10° C	50%	8 Hours	28 Hours	7 Days	28 Hours	4 weeks
15° C	50%	4 Hours	16 Hours	7 Days	16 Hours	4 weeks
25° C	50%	2 Hour	8 Hours	7 Days	8 Hours	4 weeks

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion

SPREADING RATE
with Standard Hardener
assuming no losses

7.0 square metres per litre equals 75 µm dry film thickness.

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

DUREPON® EZP

QUICKTURN® HARDENER

COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	95	170	145
Dry film per coat (µm)	50	90	75

APPLICATION CONDITIONS

	Min	Max
Air Temperature	5°C	35°C
Substrate Surface Temperature	5°C	35°C
Relative Humidity		85%

SOLIDS BY VOLUME	52.3%
VOC LEVEL	<475 g/L
POT LIFE	1.5 hours (4 litre kit, 25°C)

DRYING CHARACTERISTICS AT 75 µm DRY FILM THICKNESS* (QUICKTURN® HARDENER)

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max ¹
5° C	50%	6 Hours	10 Hours	7 Days	10 Hours	7 Days
15° C	50%	3 Hours	5 Hours	7 Days	5 Hours	7 Days
25° C	50%	1.5 Hours	2.5 Hours	7 Days	2.5 Hours	7 Days

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹If the maximum overcoat interval is exceeded then the surface **MUST** be abraded to ensure maximum intercoat adhesion.

SPREADING RATE

with Quickturn® Hardener
assuming no losses

7.0 square metres per litre equals 75 µm dry film thickness.

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM		DFT (µm)
STEEL – NEW	High corrosivity (AS2312.1 Cat C4) System EHB5	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Durepon® EZP	75 µm
			2 nd Coat	Ferreko® No. 3	125 µm
			3 rd Coat	Ferreko® No. 3	125 µm
STEEL – NEW	High corrosivity (AS2312.1 Cat C4) System PUR 3	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Durepon® EZP	75 µm
			2 nd Coat	Duremax® GPE	125 µm
			3 rd Coat	Luxathane® HPX	50 µm
STEEL – NEW	Medium – High corrosivity (AS2312.1 Cat C2-3) System ACC4	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Durepon® EZP	75 µm
			2 nd Coat	Duremax GPE	125 µm
			3 rd Coat	Acrathane® IF	50 µm
STEEL – NEW	Low - Medium (AS2312.1 Cat C2-3) System ACC2	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Durepon® EZP	75 µm
			2 nd Coat	Acrathane® IF	50 µm
STEEL – NEW	Low - Medium (AS2312.1 Cat C2-3) System PUR2	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Durepon® EZP	75 µm
			2 nd Coat	Weathermax® HBR	100 µm

NOTE: If the application is by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity

DUREPON® EZP

SURFACE PREPARATION	Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Degrease with Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's written instructions and all safety warnings. Abrasive blast clean to a minimum of AS1627.4 Class 2.5 with a blast profile of 40 – 70 microns. Remove all dust by brush or vacuum.		
APPLICATION	Mix each can thoroughly using a power mixer until the contents are uniform. Mix the contents of both packs together thoroughly using a power mixer and allow to stand for 10 minutes. Remix thoroughly before application.		
BRUSH/ROLLER	Apply even coats of the mixed material to the prepared surface. Thin if necessary with up to 50 ml/litre with Dulux® Epoxy Thinner (920-08925) or Dulux® Duthin 450 (920-81942) to ease application. Additional coats may be required to attain the specified thickness when brushing and rolling.		
CONVENTIONAL SPRAY	Thin up to 125ml/litre with Dulux® Epoxy Thinner (920-08925) or Dulux® Duthin 450 Cold Weather Thinner (920-81942) to aid atomisation.		
AIRLESS SPRAY	Typical Set-up	Graco AirPro: Pressure at Triton 308: Pressure at Gun:	1.8mm (239543) 70-100 kPa (10-15 p.s.i.) 380-410 kPa (55-60 p.s.i.)
	Standard airless spray equipment such as a Graco Xtreme 30:1 ratio with a fluid tip of 15 thou (0.38mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Thinning is not normally required but up to 50 ml/litre of Dulux® Epoxy Thinner (920-08925) may be added to ease application.		
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Freshly mixed material must not be added to material, which has been mixed for some time. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Use of fast or low temperature hardeners may result in a reduction of gloss level.		
CLEAN UP	Clean all equipment immediately after use with Dulux® Epoxy Thinner (920-08925) or Dulux® Duthin 450 (920-81942).		
OVERCOATING	Degrease with Gamlen CA 1 according to the datasheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating. Epoxies must be abraded if recoated outside the recoat window.		
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au		
STORAGE	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in a well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.		
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.		
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear a combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.		
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO ₂ or a dry chemical powder. On burning will emit toxic fumes.		
WELDING	Avoid inhalation of fumes if welding surfaces are coated with this paint. Grind off the coating before welding.		

COMPANY INFORMATION		PACKAGING, TRANSPORT AND STORAGE	
Dulux Protective Coatings is a division of		PACKAGING	Available in 15 litre packs
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	TRANSPORTATION WEIGHT	1.60 kg/litre (Average of components)
		DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 3 UN 2733
Dulux, Acrathane, Duthin, Durebild, Durepon, Ferreko, Luxathane and Weathermax are registered trade marks of DuluxGroup (Australia) Pty Ltd. Quickturn is a trade mark of DuluxGroup (Australia) Pty Ltd.			

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.