

METALSHIELD® COLD GALV PRIMER

One Pack Zinc Rich Primer

LI 002

- FEATURES**
- ZINC RICH
 - SINGLE PACK
 - FAST DRYING
 - TOUCHUP SPRAYPAKS AVAILABLE
 - CONTAINS 88% TOTAL ZINC IN THE DRY FILM

USES METALSHIELD® COLD GALV Primer incorporates a high level of finely divided zinc in the dry film providing sacrificial protection to steel substrates with the convenience of single pack application.

METALSHIELD® COLD GALV Primer is excellent for the repair of damaged galvanised steel and wrought iron balustrades and railings.

SPECIFICATIONS AS3750.9 Type 1

RESISTANCE GUIDE

WEATHERABILITY	Will chalk on exterior exposure. Use a weatherable (non-alkyd) topcoat on externally exposed steelwork.	SOLVENTS	Good resistance to splash and spillage of aliphatic hydrocarbon solvents
HEAT RESISTANCE	Up to 65°C dry heat	WATER	Resists rain and condensation. Not recommended for permanently damp or immersed exposure
SALTS	Excellent resistance to neutral salts	ALKALIS	Not recommended for use in highly alkaline conditions
ACIDS	Not recommended for acid conditions	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	Chlorinated Rubber Zinc Rich Primer		APPLICATION CONDITIONS			
FINISH	Flat		Air Temp. Substrate Temp. Relative Humidity	Min	Max	
COLOUR	Grey			5°C	40°C	
	Touchup Spraypaks available in Grey and Silver			5°C	40°C	
					85%	
COMPONENTS	One		COATING THICKNESS (MICRONS)			
VOLUME SOLIDS	42%					
VOC LEVEL	< 510g/L		Min	Max	Recommended	
FLASH POINT	24°C		Wet film per coat (µm)	120	215	180
POT LIFE	Not applicable		Dry film per coat (µm)	50	90	75
MIXING RATIO V/V	Single pack		SUITABLE SUBSTRATES			
THINNER	965-H0012	Metalshield® Cold Galv Thinner				
PRODUCT CODE	812-87306	Grey	PRIMERS	Not applicable		
			TOPCOATS	Dulux® chlorinated rubber or acrylic topcoats. (Alkyd topcoats not suitable – see Precautions)		
			APPLICATION METHODS	Conventional, airless spray or air assisted spray. Brush and roller suitable for small areas only.		

DRYING CHARACTERISTICS AT 75 µm DRY FILM THICKNESS*

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max
25° C	50%	30 Minutes	16 Hours	7 Days	3 Hours	Extended

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE
ASSUMING NO LOSSES**5.6 square metres per litre equals 75 µm dry film thickness**

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

METALSHIELD® COLD GALV PRIMER

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM		DFT (µm)
STEEL – NEW	Mild - Moderate (AS2312 Cat C2-4)	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat	Metalshield® Cold Galv Primer	75 µm
			2 nd Coat	Weathershield® Gloss	40 µm
			3 rd Coat	Weathershield® Gloss	40 µm
GALVANISED STEEL DEFECTS	Exterior/Interior	Clean, degrease and abrade surface	1 st Coat	Metalshield® Cold Galv Primer	75 µm

NOTE: If application is by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity

SURFACE PREPARATION	Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Degrease with Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's written instructions and all safety warnings. Abrasive blast clean to a minimum of AS1627.4 Class 2.5 with a blast profile of 40 – 70 microns. Remove all dust brushing or vacuum. Steel where abrasive blast cleaning is not viable: Rust, mill scale, oxide deposits and old paint films on metal surfaces must be removed by power tool cleaning according to AS1627.2 Class 2. Coating performance is proportional to the degree of surface preparation. Repair of galvanised steel: Round off all rough welds, sharp edges and zinc dags and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Remove zinc oxide deposits, rust and old paint films by power tool cleaning (AS1627.2. St 3) as a minimum. Coating performance is proportional to the degree of surface preparation. Remove all dust.
APPLICATION	Mix thoroughly using a power mixer until the contents are uniform. Remix thoroughly before and during application to prevent settlement.
BRUSH/ROLLER	For small areas only. Apply even coats to the prepared surface. Additional coats may be required to attain the specified thickness. Thin with up to 100 ml/litre with Metalshield® Cold Galv Thinner (965-H0012) if required.
CONVENTIONAL SPRAY	Thin up to 200 ml/litre with Metalshield® Cold Galv Thinner (965-H0012) to aid atomisation. Ensure paint is regularly agitated during application to prevent separation. Typical Set-up Graco AirPro: 1.8mm (239543) Pressure at Triton 308: 70-100 kPa (10-15 p.s.i.) Pressure at Gun: 380-410 kPa (55-60 p.s.i.)
AIRLESS SPRAY	Standard airless spray equipment such as a Graco Xtreme 45:1 with a fluid tip of 19-21 thou (0.48-0.53mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Ensure paint is regularly agitated during application to prevent separation. Thinning is not normally required but up to 60 ml/litre of Metalshield® Cold Galv Thinner (965-H0012) may be added to aid application.
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Consultant for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Do not apply at temperatures below 5°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Do not apply on structures subject to sustained surface temperatures above 65°C or where spillage of solvent may occur. Do not weld or flame cut through chlorinated rubber coatings. Due to their thermoplastic nature, chlorinated rubber coatings are more suited to on site application. If transporting shortly after application care should be taken to ensure painted surfaces are not in contact. NOTE: Saponifiable topcoats such as alkyds must NEVER be applied directly to Metalshield® Cold Galv Primer. NOTE: Do not thin paint with water. Do not allow water into the can, as there will be an adverse chemical reaction with the wet paint.
CLEAN UP	Clean all equipment with METALSHIELD® Cold Galv Thinner (965-H0012) immediately after use.
OVERCOATING	Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating.
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au
STORAGE	Store as required for a flammable liquid Class 3 in a bonded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO ₂ or dry chemical powder. On burning will emit toxic fumes.
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

COMPANY INFORMATION**PACKAGING, TRANSPORT AND STORAGE**

Dulux Protective Coatings a division of

DuluxGroup (Australia) Pty Ltd
1956 Dandenong Road, Clayton 3168
A.B.N. 67 000 049 427DuluxGroup (New Zealand) Pty Ltd
150 Hutt Park Road, Lower Hutt, NZ
A.B.N. 55 133 404 118**PACKAGING**Available in 1 and 4 litre cans
Available in 300g or 400g Aerosols**TRANSPORTATION WEIGHT**

2.75 kg/litre

DANGEROUS GOODSCans: Class 3 UN 1263
Aerosols Class 2 UN 1950

Dulux and Metalshield are registered trade marks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.